

TECHNICAL DATASHEET

Helmet Stickers



Helmet Stickers



TECHNICAL DATASHEET

www.ja-int.com

WHITE GLOSS VINYL

Face film: Calendered PVC Thickness: 100 micron (0.1mm)

Tensile strength: 50N/25mm MD / 48N/25mm TD

Elongation at break: 180% MD

Adhesive type: Permanent solvent-free acrylic

Adhesive weight: 18gsm

Adhesion to glass 20 mins: 13N/25mm Adhesion to glass 24 hours: 20N/25mm

Perceived tack: Medium

Application temperature: +8°C to +60°C Service temperature: -20°C to +100°C

Backing paper weight: 140gsm

Shelf life: 1 year

Fire rating: Self-extinguishing External weathering: 3 years Print: Eco-Solvent Digital Inks

CLEAR GLOSS VINYL

Face film: Monomeric calendered PVC

Thickness: 70 micron (0.07mm)

Tensile strength: 50N/25mm MD / 48N/25mm TD

Elongation at break: 180% MD

Adhesive type: Permanent clear solvent-based acrylic

Adhesive weight: 18gsm

Adhesion to glass 20 mins: 10N/25mm Adhesion to glass 24 hours: 20N/25mm

Perceived tack: Medium

Application temperature: $+5^{\circ}\text{C}$ to $+60^{\circ}\text{C}$ Service temperature: -30°C to $+110^{\circ}\text{C}$

Backing paper weight: 140gsm

Shelf life: 1 year

Fire rating: Class B. BS EN 13501-1:2007

External weathering: 5 years Print: Latex Digital Ink

CERTIFICATION

Adhesive Suitability for Helmets against Shock Absorbtion & Penetration - EN 397 JSP Approved