



**J&A (International) Limited**  
THE GARMENT DECORATION SPECIALISTS

TECHNICAL DATASHEET

# Trimax Transfers



[www.ja-int.com](http://www.ja-int.com) | +44 (0)1790 752 757

J&A (International) Ltd. Insignia House, Vale Road, Spilsby, Lincolnshire PE23 5HE

# Trimax Transfers



## TECHNICAL DATASHEET

[www.ja-int.com](http://www.ja-int.com)

### APPLICATION

Temperature (°C):	140-160°C	
Temperature (°F):	284-320°F	
Time:	10-12 seconds	
Pressure:	Medium to Low	42.7 - 56.9 psi / 2.9 - 3.9 bar / 3.0 - 4.0 kg/cm <sup>2</sup> 28.4 - 42.7 psi / 2.0 - 2.9 bar / 2.0 - 3.0 kg/cm <sup>2</sup>
Carrier Release:	Warm/Hot peel	

### LAUNDERING

Suitable for domestic wash up to 85°C  
Tumble Dry - Medium  
Iron - Medium, On Reverse  
Do Not Dry-Clean  
Do Not Bleach

### HANDLING AND STORAGE

Store in a damp-free environment at a stable temperature of ~20°C  
Keep away from direct sunlight  
No personal protection equipment is required in handling and storage  
Do not attempt to apply any transfer that has been removed from its carrier

### COMPOSITION

Ink - Solvent based  
Adhesive - Polyester  
Standard Carrier - Silicone coated parchment  
Premium Carrier - Polyester Sheeting

### HEALTH & SAFETY

This product is identified as Non-Hazardous to the end user  
No PPE is required during application\*\*

### ENVIRONMENTAL / RECYCLING

All inks are compostable  
Silicone paper carrier - Widely recyclable & Compostable  
Polyester carrier - non-recyclable  
Vegan-Friendly: No

### CERTIFICATION

Oeko-Tex: Standard 100 (Class 2)  
Flame Retardant: EN ISO 11611 & EN ISO 11612  
Colour Fastness: BS EN ISO 105  
Wash Stability: BS EN ISO 5077: 2008 & BS EN ISO 6330: 2001  
Stretch: BS EN ISO 13934-1: 1999

\*\*Any fumes created by this transfer during application are harmless. However, modern garment materials can be coated and finished in many different ways; some of which may alter their application and health & safety requirements. We recommend thorough checking and testing of any garment material to determine the correct requirements before application.